



WARRIOR[®] ROOFING MANUFACTURING

P. O. BOX 40185 • TUSCALOOSA, AL 35404 • PHONE (205) 553-1734 • FAX (205) 553-1755

193 LEROY ANDERSON ROAD • MONROE, GA 30655 • PHONE (770) 207-0695 • FAX (770) 207-0775

323 DEVELOPMENT AVENUE • CHAMBERSBURG, PA 17201 • PHONE (717) 709-0323 • FAX (717) 709-0027

SPECIFICATIONS

15 ASTM

Our #15 ASTM asphalt saturated organic felt is manufactured to meet or exceed the following :

ASTM – D226, Type I

AND AS A PREPARED ROOFING ACCESSORY CLASSIFIED BY U.L. LABORATORIES AS TO EXTERNAL FIRE EXPOSURE ONLY.

Dimensions and specifications of No. 15 ASTM asphalt felt are :

Width of roll:	36" +/-0.7%
Area:	432 sq. ft.
Net mass of saturated felt:	11.5 lbs./100 sq. ft.
Net mass of saturant:	6.2 lbs./100 sq. ft.
Saturant Weight:	Shall not be less than 1.2 times the weight of the moisture free felt.
Packaging:	The rolls are wrapped securely and the manufacturer's or distributor's name, type and specification markings are evident on the label. UPC bar coding is included on all our labels.

Updated May 2013