



WARRIOR[®] ROOFING MANUFACTURING

P. O. BOX 40185 • TUSCALOOSA, AL 35404 • PHONE (205) 553-1734 • FAX (205) 553-1755

193 LEROY ANDERSON ROAD • MONROE, GA 30655 • PHONE (770) 207-0695 • FAX (770) 207-0775

323 DEVELOPMENT AVENUE • CHAMBERSBURG, PA 17201 • PHONE (717) 709-0323 • FAX (717) 709-0027

SPECIFICATIONS

Warrior CHOICE

1 FIBERGLASS REINFORCED UNDERLAYMENT

Weight - lbs. Per 100 Square Feet	8.00
Tensile Strength	35 +/- 5
Roll Width	36" +/- 1/8"
Roll Length	133.333'
Roll Coverage	400 Sq. Ft.
Saturation	95 - 100%
Saturation Efficiency	70%
Saturant	Roofing Saturant
Base Material	Reinforced Underlayment
Felt Gauge	19.5
Mass of desaturated felt @ 100% Saturation	4.0 lbs./100 Sq. Ft.
Mass of saturant @ 100% Saturation	4.0 lbs./100 Sq. Ft.
ASTM Specification*	D-4869 Type 1

* Meets standard as U.L. prepared roofing accessory.

Updated May 2013